

European Region + 44 (0) 208 920 2306


+ 44 (0) 208 920 2306 www.energizer-eu.com

Energizer AC675 - Mercury Free



(top view) (bottom view)

Industry Standard Dimensions



Typical Discharge Characteristics

Schedule: 16 hours/day Typical Drain @ 1.3V: 2.1 & 1.3 milliamperes Load: 625 & 1,000 ohms



Simulated Application Test

Typical Performance at 21°C & 50% RH

Schedule:	Typical Drains: at 1.3V (milliamperes)	Load (ohms)	Cutoff 0.9V (hours)
16 Hours/Day	2.1	625	302
16 Hours/Day	1.3	1,000	488

Specifications

Chemical System: Zinc Air (Zn/O_2)

Tab Color:BlueDesignation:IEC-PR44Nominal Voltage:1.4 Volts

Typical Capacity: 635 mAh (to 0.9 volts)

(Rated at 326 ohms at 21°C/50% RH)

Typical Weight: 1.9 grams


Typical Volume: 0.5 cubic centimeters

Impedance


The total opposition that a battery offers to the flow of alternating current. Impedance is a combination of resistance and reactance.

The typical impedance of these cells on open circuit and during useful discharge varies from 5-20 ohms. This applies over a frequency range of 40-5,000 hertz at the current drains shown below.

Impedance vs. Frequency



Impedance vs. Depth of Discharge



Important Notice

This datasheet contains typical information specific to batteries manufactured at the time of its publication.

Contents herein do not constitute a warranty.

©Energizer Holdings, Inc. - All Rights Reserved

Form No. EBC - 8838EU Page 1 of 1