
FERROXCUBE



Supersedes data of September 2004

2008 Sep 01




E30/15/7

CORE SETS

Effective core parameters

SYMBOL	PARAMETER	VALUE	UNIT
Σ(I/A)	core factor (C1)	1.12	mm ⁻¹
Ve	effective volume	4000	mm ³
l _e	effective length	67.0	mm
A _e	effective area	60.0	mm ²
A _{min}	minimum area	49.0	mm ²
m	mass of core half	≈ 11	g



Core halves

 A_L measured in combination with a non-gapped core half, clamping force for A_L measurements 20 ±10 N, unless stated otherwise.

GRADE	A _L (nH)	μ _e	TOTAL AIR GAP (μm)	TYPE NUMBER
3C81	100 ±5% ⁽¹⁾	≈ 89	≈ 1100	E30/15/7-3C81-E100
	160 ±5%	≈142	≈ 580	E30/15/7-3C81-A160
	250 ±5%	≈ 222	≈ 330	E30/15/7-3C81-A250
	315 ±5%	≈ 280	≈ 240	E30/15/7-3C81-A315
	400 ±8%	≈ 355	≈ 180	E30/15/7-3C81-A400
	630 ±15%	≈ 560	≈ 100	E30/15/7-3C81-A630
	2500 ±25%	≈ 2220	≈ 0	E30/15/7-3C81
3C90	100 ±5% ⁽¹⁾	≈ 89	≈ 1100	E30/15/7-3C90-E100
	160 ±5%	≈142	≈ 580	E30/15/7-3C90-A160
	250 ±5%	≈ 222	≈ 330	E30/15/7-3C90-A250
	315 ±5%	≈ 280	≈ 240	E30/15/7-3C90-A315
	400 ±8%	≈ 355	≈ 180	E30/15/7-3C90-A400
	630 ±15%	≈ 560	≈ 100	E30/15/7-3C90-A630
	1900 ±25%	≈ 1690	≈ 0	E30/15/7-3C90
3C91 des	2500 ±25%	≈ 2220	≈ 0	E30/15/7-3C91
3C92 des	1400 ±25%	≈ 1250	≈ 0	E30/15/7-3C92
3C94	1900 ±25%	≈ 1690	≈ 0	E30/15/7-3C94
3C96 des	1600 ±25%	≈ 1 420	≈ 0	E30/15/7-3C96

E30/15/7

GRADE	A _L (nH)	μ _e	TOTAL AIR GAP (μm)	TYPE NUMBER
3F3	100 ±5% ⁽¹⁾	≈ 89	≈ 1100	E30/15/7-3F3-E100
	160 ±5%	≈142	≈ 580	E30/15/7-3F3-A160
	250 ±5%	≈ 222	≈ 330	E30/15/7-3F3-A250
	315 ±5%	≈ 280	≈ 240	E30/15/7-3F3-A315
	400 ±8%	≈ 355	≈ 180	E30/15/7-3F3-A400
	630 ±15%	≈ 560	≈ 100	E30/15/7-3F3-A630
	1600 ±25%	≈1420	≈ 0	E30/15/7-3F3
3F35 des	1250 ±25%	≈1110	≈ 0	E30/15/7-3F35

Note

1. Measured in combination with an equal gapped core half, clamping force for AL measurements, 20 \pm 10 N.

Core halves of high permeability grades

Clamping force for A_L measurements 20 ± 10 N.

GRADE	A _L (nH)	μ _e	AIR GAP (μm)	TYPE NUMBER
3C11	3300 ±25%	≈ 2930	≈ 0	E30/15/7-3C11
3E27	4100 ±25%	≈ 3640	≈ 0	E30/15/7-3E27

Properties of core sets under power conditions

	B (mT) at		CORE LOSS (W) at				
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 100 kHz; B = 200 mT; T = 100 °C	f = 400 kHz;		
3C81	≥320	≤ 0.82	_	_	_		
3C90	≥330	≤ 0.45	≤ 0.48	_	-		
3C91	≥320	-	$\leq 0.27^{(1)}$	≤ 1 .6 ⁽¹⁾	-		
3C92	≥370	_	≤ 0.36	≤ 2.0	-		
3C94	≥330	-	≤ 0.36	≤ 2.0	-		
3C96	≥340	_	≤ 0.27	≤ 1.6	-		
3F3	≥320	_	≤ 0.47	-	≤ 0.80		
3F35	≥300	_	_	_	_		

Properties of core sets under power conditions (continued)

	B (mT) at		CORE LOS	S (W) at	
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 500 kHz; B = 50 mT; T = 100 °C	f = 500 kHz; B = 100 mT; T = 100 °C	f = 1 MHz; Ĥ = 30 mT; T = 100 °C	f = 3 MHz; B = 10 mT; T = 100 °C
3C96	≥340	≤ 1.5	-	-	-
3F3	≥320	_	_	_	_
3F35	≥300	≤ 0.54	≤4.2	-	-

Note


1. Measured at 60 $^\circ\text{C}.$

2008 Sep 01

COIL FORMERS

GENERAL DATA FOR E30/15/7 COIL FORMER WITHOUT PINS

PARAMETER	SPECIFICATION
Coil former material	polyamide (PA6.6), glass reinforced, flame retardant in accordance with <i>"UL 94-HB"</i> ; UL file number E41613(M)
Maximum operating temperature	120 °C




WINDING DATA AND AREA PRODUCT FOR E30/15/7 COIL FORMER WITHOUT PINS (E)

NUMBER OF SECTIONS	WINDING AREA (mm²)	MINIMUM WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm ⁴)	TYPE NUMBER
1	80	17.0	56	4800	CP-E30/15/7-1S

E30/15/7

GENERAL DATA FOR 10-PINS E30/15/7 COIL FORMER

PARAMETER	SPECIFICATION
Coil former material	phenolformaldehyde (PF), glass reinforced, flame retardant in accordance with <i>"UL 94V-0"</i> ; UL file number E167521(M)
Pin material	copper-tin alloy (CuSn), tin (Sn) plated
Maximum operating temperature	180 °C, <i>"IEC 60085"</i> , class H
Resistance to soldering heat	"IEC 60068-2-20", Part 2, Test Tb, method 1B: 350 °C, 3.5 s
Solderability	<i>"IEC 60068-2-20"</i> , Part 2, Test Ta, method 1: 235 °C, 2 s



WINDING DATA AND AREA PRODUCT FOR 10-PINS E30/15/7 COIL FORMER (E)


NUMBER OF NECTIONS	WINDING AREA (mm²)	MINIMUM WINDING WIDTH (mm)	AVERAGE LENGTH OF TURN (mm)	AREA PRODUCT Ae x Aw (mm ⁴)	TYPE NUMBER
1	80	17.1	56	4800	CSH-E30/15/7-1S-10P

E30/15/7

MOUNTING PARTS

General data and ordering information

ITEM	REMARKS	FIGURE	TYPE NUMBER
Clasp	CuZn alloy, Ni plated	4	CLA-E30/15/7
Spring	stainless steel (CrNi)	5	SPR-E30/15/7



DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.